

Abstract:

The present invention relates to a method of manufacturing a paper of multi-colour ink-jet printable grade. A proper hydrophicity for the paper is secured by using an 2-oxetanone size in the appropriate sizing steps. The size is made from non-branched and branched-chain fatty acids having main chain comprising 6-22 carbons linked with each other by saturated bonds.

09895160-070201